

Report Date: 21/02/2024

## Analysis Report: ST24-00253.001 Reissue: 1

**\*\* This Amended Report cancels and supersedes the Report No. ST24-00253.001 Dated 01/02/2024 issued by SGS.**

BESTON GROUP CO.,LTD.  
NO.905, 9TH FLOOR, BLOCK A, NO.99 SOUTH  
UNIVERSITY ROAD. ERQI DISTRICT, ZHENGZHOU CITY,  
HENAN PROVINCE  
CHINA

The results shown in this test report specifically refer to the sample(s) tested as received unless otherwise stated. All tests have been performed using the latest revision of the methods indicated, unless specifically marked otherwise on the report. Precision parameters apply in the determination of the below results. Users of analytical results, when establishing conformance with commercial or regulatory requirements should note the full provisions of ASTM D3244, IP 367 and ISO 4259 in that context, the default confidence level of petroleum testing having been set at the 95% confidence level. Your attention is specifically drawn to Sections 7.3.6., 7.3.7 and 7.3.8 of ASTM D3244. With respect to the UOP methods listed in the report below the user is referred to the method and the statement within it specifying that the precision statements were determined using UOP Method 999. This Test Report is issued under the Company's General Conditions of Service (copy available upon request or on the company website at www.sgs.com). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. This report shall not be reproduced except in full, without the written approval of the laboratory.

The sample(s) and information was/were submitted and confirmed by the client or by a third party acting at the client's direction. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client. The findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample.

JOB ORDER NO. :	COBOCJ2400052-01BT	BOSS ORDER NO.:	--
SAMPLE SOURCE :	Supplied by Client	PRODUCT DESCRIPTION :	Oil - pyrolysis oil from waste tire(after filtration)
SAMPLE TYPE :	--	SAMPLE BY :	Client
SAMPLED :	--	RECEIVED :	17/01/2024
ANALYSED :	31/01/2024	COMPLETED :	31/01/2024
SAMPLE OBTAIN WAY:	Logistics delivery to SGS	SAMPLE STATE:	Liquid in Plastic Bottle
CONTAINER:	1×1L Plastic Bottle		
SAMPLE COMMENT :	update content:customers require change the product name		
REPORT COMMENT :	The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.		

PROPERTY	METHOD	RESULT UNITS	MIN	MAX
Density at 20°C	ASTM D4052-22	0.9331 g/cm³	--	--
Kinematic Viscosity at 40°C	ASTM D445-23	5.084 mm²/s	--	--
Kinematic Viscosity at 100 °C	ASTM D445-23	0.7058 mm²/s	--	--
Pour Point	ASTM D97-17b(2022)	<-57 °C	--	--
Cleveland Flash Point (Open cup)	ASTM D92-18	<79 °C	--	--
Gross Heat of Combustion	ASTM D240-19	40.495 MJ/kg	--	--
Ash from Petroleum Products	ASTM D482-19			
Ash		0.010 % (m/m)	--	--
Total Sulfur Content	ASTM D4294-21	0.681 % (m/m)	--	--
Acid Number (Inflection end-point)	ASTM D664-18e2(Method A)	0.8 mg KOH/g	--	--
Elements in Residual Fuel Oil by ICP	IP 501/05(2019)			
Aluminium		<5 mg/kg	--	--
Calcium		<3 mg/kg	--	--
Phosphorus		9 mg/kg	--	--
Vanadium		<1 mg/kg	--	--
Zinc		1 mg/kg	--	--
Iron		32 mg/kg	--	--
Sodium		<1 mg/kg	--	--
Nickel		<1 mg/kg	--	--
Potassium §		<1 mg/kg	--	--
Magnesium §		<1 mg/kg	--	--
Lead §		<1 mg/kg	--	--

§ - Analyte not in published method scope

REPORTED BY

Calvin Wang  
Chemist

2102202415130000223239

AUTHORISED SIGNATORY

Demin Wang  
Lab Manager

Page 1 of 2



OGC-EN\_REPORT-2017-07-11\_v60e

Report Date: 21/02/2024

## Analysis Report: ST24-00253.001 Reissue: 1

**\*\* This Amended Report cancels and supersedes the Report No. ST24-00253.001 Dated 01/02/2024 issued by SGS.**

BESTON GROUP CO.,LTD.  
NO.905, 9TH FLOOR, BLOCK A, NO.99 SOUTH UNIVERSITY ROAD. ERQI DISTRICT, ZHENGZHOU CITY, HENAN PROVINCE  
CHINA

PROPERTY	METHOD	RESULT UNITS	MIN	MAX
Elements by ICP	ASTM D5185-18(Modified)			
Silicon Content		<10 mg/kg	--	--
Flash Point by PMCC	ASTM D93-20(Procedure A)	<40 °C	--	--
----- End of Analytical Results -----				

This document is only valid in its entirety and your attention is drawn to the Terms and Conditions on Page 1 of this report.

REPORTED BY

AUTHORISED SIGNATORY

Calvin Wang  
Chemist

Demin Wang  
Lab Manager



2102202415130000223239

Page 2 of 2

OGC-EN\_REPORT-2017-07-11\_v60e