



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

日期Date: 2025/4/11 送样人Sender: 李庆龙

样品资料/Sample information:

样品名称 Name	Indonesian Tires	送样重量 Weight	—
样品状态 Sample status		取样重量 Sampling weight	200g
实验用时 Time	1h54min	实验温度 Temperature	371℃

实验过程Experimental process:

催化裂解

序号 No.	时间段 Time	烟气温度 Flue gas	备注 Remark
1	13:56	21℃	Start heating
2	14:08	34℃	Start emitting smoke
3	14:14	83℃	Oil starts to come out
4	14:16	129℃	Accelerate oil output
5	14:20	213℃	Large amounts of smoke
6	14:29	339℃	Oil output slows down
7	14:45	336℃	Stop oil discharge
8	15:50	226℃	Stop heating

实验结果/Result:

项目 Item	组成 Composition	单位/g Unit/g	占比量/% Ratio/%
	Pyrolysis oil	90g	45.00%
	Carbon black	73g	36.50%
	Combustible gas	37g	18.50%

实验总结

Test summary

备注:
以上数据仅供参考
Noted:
The above data is for reference only



BESTON GROUP CO., LTD
9 FLOOR, 6 BUILDING, E-COMMERCIAL PORT OF CENTER,
ZHENGZHOU CITY, CHINA
TEL: 0086-371-55181866 WEB: www.bestongroup.com

Raw material pictures



Oil sample pictures



Carbon black pictures

